

- The Original Copper-free Antifouling Paint!
- “Recommended” and “24 Month Finalist” ratings by Practical Sailor Magazine, October 2009 Issue
- Better antifouling performance and protection than other copper-free paints
- Available in Bright Colors & True White - does not discolor like competitors ePaint-like products
- Hybrid finish incorporates benefits of both hard and ablative type paints - no old paint build up
- Unlimited coat to launch time
- Perfect for any boat, out-drives, and running gear

GENERAL DESCRIPTION



ePaint ZO is the original copper-free antifouling paint and is designed for all boat types including sailboats, powerboats, and commercial workboats. ZO is available in many colors including a bright white that stays true and does not discolor like the competitor products do. ePaint ZO is easy to apply and is compatible over most popular bottom paints. Like all ePaint's, ZO is copper-free and will not promote corrosion on aluminum hulls or metal parts. Rather than following the archaic method used to leach toxicants into our waters, ZO prevents bio-fouling combining a patented photoactive process and actives that do not persist.

APPLICATION INFORMATION

ZO may be applied by traditional painting techniques. Follow instructions set forth in this technical data sheet for detailed information for your particular application.

SURFACE PREPARATION

Proper surface preparation is an important step for a coating system that performs properly and lasts. Follow recommendations set forth in following sections carefully. Inadequate surface preparation will result in poor coating performance.

MAINTENANCE

No antifouling paint can be effective under all conditions of exposure. Pollution and natural occurrences can adversely affect antifouling paint. Extreme air and water temperatures, silt, dirt, oil, poor water clarity, and low oxygen levels can harm antifouling paint. Therefore, ePaint suggests that the bottom of the boat be checked regularly to make sure it is clean and that no growth is occurring. Lightly scrub the bottom with a cloth or soft brush to remove anything from the antifouling paint surface. Scrubbing is particularly important to boats that sit idle for extended periods of time in high fouling bodies of water. Antifouling paints are general more effective when the boat is used periodically.

PHYSICAL DATA

COLORS:

001 YELLOW	
101 BLUE	
201 GREEN (TEAL)	
301 BLACK	
401 WHITE*	
501 RED (BRIGHT)	
701 GRAY*	
901 SAFETY ORANGE	

*Most photoactive, best for high-fouling & tropical waters

PACKAGING: Quart, gallon, 5 gallon pail

VEHICLE TYPE: Solvent

CURING MECHANISM: Evaporation

SOLIDS BY VOLUME: 55% ± 2%

THEORETICAL COVERAGE: 310 ft²/gal

VOC: <400 g/L

FLASH POINT: 82°F (28°C) Setaflash

STORAGE: Between 38°F and 80°F

ACTIVE INGREDIENT: Zinc Omadine®, 4.8%

APPLICATION DATA

METHOD: Brush, roller (3/8" nap), or spray
 NUMBER OF COATS: 2 or 3 full coats with additional coats at waterline and leading edges (e.g. bow, keel, rudder, chines)
 DRY FILM THICKNESS: 3-4 mils per coat
 WET FILM THICKNESS: 5-7 mils per coat
 APPLICATION TEMP: 45°F to 90°F
 DRY TIMES (HOURS)*:

Temp	To Re-coat	To Launch
90°F	3	14
70°F	4	16
55°F	8	24

*The above dry times are minimums. Re-coat within 7 days to avoid additional surface prep (i.e. sanding)

DRY TO LAUNCH TIME: Not critical

THINNER: EP-13 or EP-15, 20% max by vol

CLEAN-UP: EP-13, EP-15, Xylene, or MEK

COMPANION PRODUCTS

- EP-PRIME 1000, multi-purpose use epoxy primer 
- EP-STRIP, water-based, non-caustic paint/varnish remover 
- eProp & EP-21 Aerosol, for props & running gear 
- EP-13 and EP-15 thinners, for reduction and clean up 

APPLICATION DETAILS

Mix ePaint ZO thoroughly before use to ensure materials are uniformly dispersed throughout the can as settling of solids can occur. All surfaces to be painted shall be clean prior to sanding and painting. Visit www.epaint.com or contact an ePaint Technical Representative for answers to questions regarding application and compatibility.

PREVIOUSLY PAINTED SURFACES: ZO is compatible over most popular antifouling paints and epoxy-type barrier coatings that are in good condition. All loose, cracking, peeling, and flaking paint should be removed. Thoroughly wash clean and then abrade existing paint with 80 grit sandpaper, wipe away dust and debris, and allow to air dry. Following instructions set forth in the Application Data section on the opposite page, apply two or three full coats with additional coats around the waterline and leading edges. For ultimate adhesion, remove existing bottom paint down to fiberglass or existing barrier coat and apply a tie-coat of ePaint EP-Prime 1000 epoxy following instructions in the following section.

FIBERGLASS: ZO may be applied directly to bare, abraded gel-coat. Optionally, ePaint EP-Prime 1000 multi-purpose epoxy primer may be used for improved adhesion and to reduce the potential for water migration on boats that are in service year round. Take care to thoroughly clean and remove all mold release agents and boat finishing wax residue prior to sanding; mechanically abrade with 80 grit sandpaper to create a dull matte finish, wipe away all dust / debris.

GOOD: Apply ZO directly to bare, abraded gel-coat. Following instructions set forth in the Application Data section on the opposite page apply two or three full coats with additional coats around the waterline and leading edges.

BETTER: Apply one tie-coat of EP-Prime 1000 epoxy primer for improved adhesion. The first coat of ZO shall be applied when the final coat primer is *tack-free but soft-to-finger pressure*. If window is missed apply another coat of EP-Prime 1000. The next day to within one week, following information set forth in the Application Data section on the opposite page apply a total of two or three full coats of ZO with additional coats around the waterline and leading edges.

BEST: Fiberglass boat bottoms are potentially susceptible to water migration and can potentially form osmotic blisters within the gelcoat and into the laminate. To render the bottom as water impermeable as possible, apply three full coats of ePaint EP-Prime 1000 epoxy primer. The first coat of ZO shall be applied when the last coat epoxy primer is *tack-free but soft-to-finger pressure*. If window is missed apply another coat of EP-Prime 1000. The next day to within one week, following information set forth in the Application Data section on the opposite page apply a total of two or three full coats of ZO with additional coats around the waterline and leading edges.

ALUMINUM & STEEL: ePaint ZO is safe for use on aluminum and steel as it will not promote galvanic corrosion. Aluminum and steel surfaces must be primed with ePaint EP-Prime 1000 corrosion inhibiting epoxy primer. All direct to metal coatings provide maximum performance over blasted surfaces. Metal surfaces should be prepared to no less than a near-white metal cleanliness in accordance with NACE 2/SSPC-SP-5/SA 2.5 specifications. Abrasive blast or mechanically abrade with 80 grit aluminum oxide sandpaper to achieve a 1.5-2.5 mil (38-63 micron) depth profile in a sharp, jagged pattern as opposed to a peen pattern from shot-blasting; *immediately* prime with EP-Prime 1000 corrosion inhibiting epoxy primer. Apply final coat of EP-Prime 1000 next day to within one week. The first coat of ZO shall be applied when the final coat of epoxy primer is *tack-free but soft-to-finger pressure*. If window is missed apply another coat of EP-Prime 1000. The next day to within one week, following information set forth in the Application Data section on the opposite page apply a total of two or three full coats of ZO with additional coats around the waterline and leading edges.

WOOD: Clean and abrade surface with 80 grit sandpaper and wipe away all dust and debris. Reduce first coat of ZO 20% by volume with ePaint EP-13 or EP-15 VOC exempt thinner and allow to dry overnight. The next day to within one week, following information set forth in the Application Data section on the previous page apply a total of two or three full coats of ZO with additional coats around the waterline and leading edges. Not compatible over silicone-based fillers.

TIPS: Due to the photo-active nature of ZO, lighter colors offer better antifouling protection in high fouling areas (e.g. tropics and murky waters) and additional coats around the waterline are strongly recommended to extend coating service life. Stripe coating high wear areas and leading edges such as the bow, keel, rudder, chines and sterngear is also recommended to extend coating service life. ZO viscosity will increase at cooler temperatures and over time; if necessary reduce with EP-13 or EP-15 VOC exempt thinner to ease application.

SAFETY: See individual label for health and safety data. MSDS may be requested by contacting ePaint Company.

ePaint Company • 25 Research Road, East Falmouth, MA 02536 • 800-258-5998 • www.epaint.com

Information in this technical data sheet is not intended to be exhaustive and is subject to modification from time to time in the light of experience and our policy of continuous product development. Please visit www.epaint.com for the most recent product information.